



DESCRIPTION

			PureClean
Total thickness	EN 428	mm	2.90
Thickness of the wear-layer	EN 429	mm	0.30
Weight / Mass per unit area	EN 430	g/m ²	2170
Width of sheet	EN 426	cm	200 / 300 / 400
Length of sheet	EN 426	ml	± 25
Surface treatment	-	-	PureClean

CLASSIFICATION

Norm / Product specification	-	-	EN 653
European classification	EN 685	class	23-31
Fire rating - Classification	EN 13501-1	class	C _{fl} -s1
Wear group	EN 653	group	T

PERFORMANCES

Impact sound insulation	EN ISO 717-2	dB	16
Dimensional stability after exposure to heat	EN 434	%	0,05
Residual Indentation	EN 433	mm	0,20
Colour fastness	EN 20 105 - B02	degree	≥ 6
Guarantee			15 years

CE MARKING

CE	EN 14041	



Areas of use: domestic